

**DECORATIVE & PROTECTIVE PAINTS
PRODUCT DATA SHEET**

**DR.WOOD POLIURETHANE
HARDENER**



DESCRIPTION

Aromatic polyisocyanate based, polyurethane furniture varnish hardener.

FEATURES

RECOMMENDED APPLICATION FIELDS

It is a hardener component used in preparation of Dr. Wood Polyurethane WP.236,WP.237,WP.238,WP.239,WP.242,WP.243,WP.244,WP.246 series furniture paint and varnishes. Do not use only this product alone.

CHARACTERISTICS

PAINT FILM Polymeric Isocyanate
SPECIFIC GRAVITY 0,98-0,99 kg/lt
SOLID CONTENT(%By Weight) 32-34
FLASH POINT 21°C

SHELF LIFE Minimum 9 months in unopened original box
STORAGE TEMPERATURE It is best suited for indoors with no direct sunlight between 5 ° C and 35 ° C.

APPLICATION			APPLICATION CONDITIONS
WP.236.0000 HS.245.0033	100 Units 50 Units	(By Weight)	Temperature (air, surface, Product): 15 ° C minimum, 35 ° C maximum At least 3 ° C above dew point Relative Humidity: 85% maximum
WP.237.0000 HS.245.0033	100 Units 50 Units	(By Weight)	
WP.238.0000 HS.245.0033	100 Units 50 Units	(By Weight)	CERTIFICATES / APPROVALS
WP.239.0000 HS.245.0033	100 Units 33 Units	(By Weight)	ADDITIONAL INFORMATION
WP.242.0000 HS.245.0033	100 Units 100 Units	(By Weight)	HEALTH AND SAFETY
WP.243.0000 HS.245.0033	100 Units 25 Units	(By Weight)	Read the Safety Data Sheet before use. CST reserves the right to change the technical document. Contact our technical service department for more information.
WP.244.0000 HS.245.0033	100 Units 25 Units	(By Weight)	
WP.246.0000 HS.245.0033	100 Units 100 Units	(By Weight)	WARRANTY
			CST guarantees that this product is manufactured in accordance with the standards and without any error. In the event of a proven manufacturing defect, CST will replace the defective product or refund the fee. Under no circumstances, CST does not provide warranties.

Disclaimer

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of CST Kimya A.Ş. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the products herein must be determined exclusively by the Buyer and/or User. Product information are provided "as is" and to the extent permitted by law, without any kind of guarantee, commitment or liability. Except in case of willful misconduct, CST Kimya A.Ş is not liable for damages that are caused by or in connection with the use of this information. In any case, CST Kimya A.Ş is not responsible for and assumes no liability for any indirect, incidental or consequential damages that are caused by or in connection with the use of such content.